

AS 26

SAW Wires

C-Mn and low-alloy steels



Classification

EN ISO	14171-A-S1
AWS	A5.17: EL 12

Chemical analysis (Typical values in %)

C	Mn	Si	P	S
0.1	0.5	0.1	≤ 0.02	≤ 0.02

Packaging data

Packaging Type	B450
Diam(mm) / weight(kg)	25
1.6	●
2.0	●
2.4	●
3.2	●
4.0	●

AS 35

SAW Wires

C-Mn and low-alloy steels



Classification	
EN ISO	14171-A-S2
AWS	A5.17: EM 12K

Chemical analysis (Typical values in %)

C	Mn	Si	P	S
0.1	1	0.12	≤0.025	≤0.025

Packaging data

Packaging Type	B300	B450	DRUM
Diam(mm) / weight(kg)	16	25	300
1.6	●		
2.0		●	●
2.4		●	●
3.2		●	●
4.0		●	●
4.8		●	

AS 37LN

SAW Wires

C-Mn and low-alloy steels



Classification

EN ISO	14171-A-S3Si
AWS	A5.17: EH 12K

Chemical analysis (Typical values in %)

C	Mn	Si	P	S	Cu
0.1	1.7	0.3	≤0.015	≤0.015	0.04

Packaging data

Packaging Type	B450	B570	DRUM
Diam(mm) / weight(kg)	25	90	300
2.4	●		●
3.2	●		●
4.0	●	●	●